



FILTER MEDIA DATA

100% Cellulose Media

Origin of media	American
Features	Good water resistance, special colors and contains synthetic fiber
Basis weight	141 g/m ²
Overall caliper	0.762 mm
Corrugation Depth	0.35mm
Mullen Burst	176 Kg/cm ² , 172 Kpa
Mean pore diameter	21 microns
Cured resin content	22 percent
Gurley Stiffness	3500 MG
Tensile	MD (dry) 5.25 KN/m; CD (dry) 1.75 KN/m
Pressure Drop	27 mm/sec @4000cm ³ /sec per 100 cm ²

Add: 1 GuoTai Road, Zhangjiagang, Jiangsu Province, China P.C.: 215600

Tel: +86-512-5868 5979 Fax: +86-512-5898 6893

www.industrialcleanair.com

Email: airmaxfilter@yahoo.com.cn MSN: fullcart@hotmail.com