



FILTER MEDIA DATA

Cellulose/Polyester Blend Media

Origin of media	American
Features	Heavy duty air filtration, Low energy
Basis weight	131.8 g/m ²
Overall caliper	0.711 mm
Corrugation Depth	0.406mm
Permeability/CFM	112 L/sm/sec@20mm WG
Max pore diameter	48 microns
Cured resin content	22 percent
Stiffness	MD (dry) 2451MG; CD (dry) 538MG
Tensile	MD (dry) 45.20lbs/inch; CD (dry) 16.70lbs/inch
Special Fibers	Polyester 20 percent

Add: 1 GuoTai Road, Zhangjiagang, Jiangsu Province, China P.C.: 215600

Tel: +86-512-5868 5979 Fax: +86-512-5898 6893

www.industrialcleanair.com

Email: airmaxfilter@yahoo.com.cn MSN: fullcart@hotmail.com