



## FILTER MEDIA DATA

### Cellulose/Polyester Blend Flame Retardant

Origin of media	American
Features	Heavy duty air filtration, Low energy
Basis weight	154.6 g/m <sup>2</sup>
Overall caliper	0.711 mm
Corrugation Depth	0.406mm
Permeability/CFM	112 L/sm/sec@20mm WG
Max pore diameter	50 microns
Cured resin content	39 percent
Stiffness	MD (dry) 2552MG; CD (dry) 578MG
Tensile	MD (dry) 35.40lbs/inch; CD (dry) 15.40lbs/inch
Special Fibers	Polyester 20 percent

Add: 1 GuoTai Road, Zhangjiagang, Jiangsu Province, China P.C.: 215600

Tel: +86-512-5868 5979 Fax: +86-512-5898 6893

[www.industrialcleanair.com](http://www.industrialcleanair.com)

Email: [airmaxfilter@yahoo.com.cn](mailto:airmaxfilter@yahoo.com.cn) MSN: [fullcart@hotmail.com](mailto:fullcart@hotmail.com)