

### 100% Polyester + PTFE Media

Origin of media	America
Features	High Efficiency expanded PTFE membrane on polyester media
Scrim composition	Thermally fused polyester
Basis weight	260 g/m <sup>2</sup>
Thickness	0.60 +/-10% mm
Weight after bonding	280 g/m <sup>2</sup>
Thickness	0.33~0.83mm
Air permeability	25~45 l/dm <sup>2</sup> /min @ 200 pa 2.6~4.8 cc/cm <sup>2</sup> /s @ 12.7 mmH <sub>2</sub> O
Minimum Mullen burst	14kg/cm <sup>2</sup>
Minimum breaking strength	Warp: 441N/50mm Weft: 245N/50mm
Minimum breaking strength	Warp: 45kg/50mm Warp: 25kg/50mm
Continuous service temperature	135 °C
Finish	Microporous PTFE membrane

Add: 1 GuoTai Road, Zhangjiagang, Jiangsu Province, China P.C.: 215600

Tel: +86-512-5868 5979 Fax: +86-512-5898 6893

[www.industrialcleanair.com](http://www.industrialcleanair.com)

Email: [airmaxfilter@yahoo.com.cn](mailto:airmaxfilter@yahoo.com.cn) MSN: [fullcart@hotmail.com](mailto:fullcart@hotmail.com)