FILTER MEDIA DATA

100% Spun Bond Polyester

Origin of media	Japan
Basis weight	270 +/-10% g/m2
Thickness	0.60 +/-10% mm
Tensile strength	MD 118.53; CD 61.83 N/50mm
Bending Rigidity	561.33 gr
Pore Size	Max: 68.5 Mean: 51.8 microns
Bursting Strength	24.67 kgf
Air Permeability	27 cc/cm2/sec

Add: 1 GuoTai Road, Zhangjiagang, Jiangsu Province, China P.C.: 215600

Tel: +86-512-5868 5979 Fax: +86-512-5898 6893

www.industrialcleanair.com

Email: airmaxfilter@yahoo.com.cn **MSN:** fullcart@hotmail.com